



RD White

TECHNICAL DATA SHEET

RD White

General: *It is a water based printing base that has high colour and soft touching white effect used by discharging the color of the dischargeable fabric in textile printing.*

Technical Details :

Appearance	: Paste
Odor	: Characteristic
Color	: White
Viscosity	: [(77 °F) sp: 6, rpm: 20 Brookfield] : 15.000 – 35.000 [mPa.s]
Density	: 1,27 g/cm ³ (77 °F)
pH	: 7.5 - 8.5
Boiling Point	: >212°F
Solubility	: Soluble in water

(Standards: for fastness tests - ISO 105-X10: 1993 / ISO 105-D01:2010 / ISO 105-B02:2013)

Advantages :

If used correctly as advised, the dry-wet rubbing and washing fastness are high.

RD White provides to extremely soft touching effects. Easy using during the print.

It is a discharge printing products.

Suitable to ecological standards.

Applications :

Rubbing and washing tests should be applied 24 hours after curing.

Never use water to reduce the viscosity. Before use, please stir the product well.

Do not use any additives that are not advised. After using, the screen should be cleaned with the water.

Usage :

It is advised to mix with RD Clear Base.

It provides to print with the silk-screen that are made between 43-77 mesh.



RD White

TECHNICAL DATA SHEET

50 – 62 Shore U type dr. blade should be used.

Packaging Information :

Ecoflex D 10 is packed in 30 kg and 60 kg plastic cans.

Storage & Shelf Life :

Keep containers dry and tightly closed. Store in a ventilated place between (+5)-(+30) °C/(+41)-(+86)°F of temperature.

It should be consumed within 2 years after the production date.

Important :

The technical application and information that have been given above, are designed only as using instructions. Should not be considered as a warranty for any other use. When any help or assistance is required, our technical department is ready for help.

In case of emergency, Safety Data Sheet of this product should be ready for help at the working area.

The warnings are given on safety data sheet of this product is for use outside the manufacturer/ distributor to direct/indirect can not be held responsible for any loss or damage.